

Lotrène® FB5026

LOW DENSITY POLYETHYLENE

DESCRIPTION

Lotrène® FB5026 is mainly recommended for heavy duty film applications with good optical properties. It contains additive that gives good slip properties.

PROPERTIES

The suitable molecular structure of Lotrène® FB5026 makes it possible to produce very thin, clear and glossy films.

Lotrène® FB5026 produces films that are very strong, sufficiently rigid for automatic packaging machines, suitable for shrink wrapping and have good dimensional stability.

POLYMER PROPERTIES	VALUE	UNIT	TEST METHOD
Melt Flow Index	0.60	g/10 min.	ASTM D-1238
Density @ 23 °C	0.920	g/cm ³	ASTM D-1505
Crystalline Melting Point	108	°C	ASTM E-794
Vicat Softening Point	93	°C	ASTM D-1525

FILM PROPERTIES	VALUE	UNIT	TEST METHOD
Tensile Strength @ Yield MD/TD	14/11	MPa	ASTM D-882
Tensile Strength @ Break MD/TD	24/24	MPa	ASTM D-882
Elongation @ Break MD/TD	550/600	%	ASTM D-882
Impact Strength, F 50	200	G	ASTM D-1709
Coefficient of Friction	0.20	-	ASTM D-1894
Haze	11	%	ASTM D-1003
Gloss (@ 45 °)	45	GU	ASTM D-2457
Clarity	45	%	ASTM D-1746

(The above properties are measured on a blown film of 50 µ, @ 2.5 BUR)

FB5026



Lotrène® FB5026

LOW DENSITY POLYETHYLENE

Note: The values given in this technical data sheet are the results of tests carried out in accordance with standard test procedures. They are given as indication to enable customers to make the best use of our products but must be considered as average values provided without implying any undertaking on our part.

PROCESSING

Lotrène® FB5026 can be easily processed on all types of extruders designed for polyethylene.

The melt temperature is suggested to be in the range of 160-180 °C.

The best properties of the blown film are achieved at blow up ratios between 2.5:1 and 3.5:1.

To avoid blocking and shrinkage on the reel, the temperature at the nip rolls and take-off should be kept as close as possible to the ambient temperature. The recommended thickness range is from 40 µm 200 µm.

APPLICATIONS

- Shopping bags
- Medium duty carrier bags
- Milk bags (pouches)
- Industrial liners

SAFETY AND STORAGE

Under normal conditions Lotrène® FB5026 does not present a toxic hazard through skin contact or inhalation. During processing, contact with molten polymer and inhalation of volatilized fumes should be avoided.

Lotrène® FB5026 complies with food grade regulations FDA, 21 FR chapter 177-1520 'Olefin Polymers'. Items made from this grade do not transmit tests nor odor to the material in contact with.

Lotrène® FB5026 is inflammable and combustible (category 3) according to ISO R 1210.

Lotrène® FB5026 is supplied in plastic bags of 25 kg (net weight) each. The bags are stacked and shrink wrapped on pallets of 1500 kg each (net weight). The product is forwarded either by trucks or in 20-foot sea containers.

Lotrène® FB5026 should not be stored for more than three months nor be exposed to direct sunlight and/or heating during storage since this may adversely affect the properties of the product.

FB5026

