

## HEAD OFFICE:

Plot No. – 12, Sector B1,

Local Shopping Complex, Vasant Kunj,

New Delhi - 110 070 (INDIA). Tel: 0091-11-26139256 – 265

Fax: 0091-11-26125739
Web site: www.jindalpoly.com

TECHNICAL DATA SHEET (J-950)

**DESCRIPTION:** Bi-axially oriented translucent direct matte polyester film with medium surface gloss and thermally stable.

**APPLICATIONS:** Muted metallization, wood grain application, label and other industrial application. **SALIENT FEATURES:** 

- Medium surface gloss
- Excellent Mechanibility
- Excellent Mechanical and thermal Properties

		TECHNICAL DATA					
Properties		Test method	Unit	J950			
PHYSICAL							
Thickness		ASTM D-374	Micron	12	23	36	50
Grammage		JPFTM	gm/m <sup>2</sup>	16.8	32.2	50.4	70
Yield		JPFTM	m <sup>2</sup> / kg	59	31	20	14
OPTICAL							
Haze (Min)		ASTM D-1003	%	48	70	80	85
Transmittance		ASTM D-1003	%	85 <u>+</u> 3	83 <u>+</u> 3	81 <u>+</u> 3	79 <u>+</u> 3
Gloss at 60 degree angle (Average)		ASTM D 2457	%	40 <u>+</u> 5	40 <u>+</u> 5	42 <u>+</u> 5	42 <u>+</u> 5
MECHANICAL							
Tensile strength (Min)	MD	ASTM D-882	Kg/cm <sup>2</sup>	1900	1800	1800	1800
	TD	ASTM D-882	Kg/cm <sup>2</sup>	1800	1700	1700	1700
Elongation (Min)	MD	ASTM D-882	%	90	90	90	90
	TD	ASTM D-882	%	90	90	90	90
Coefficient of friction (Side-A / B) (Max)	St	ASTM D-1894		0.45	0.45	0.45	0.45
	Dy	ASTM D-1894		0.40	0.40	0.40	0.40
THERMAL							
Shrinkage (Max) (150°C / 30 min)	MD	ASTM D-1204	%	2.80	2.80	2.80	2.80
	TD	ASTM D-1204	%	0.40	0.40	0.40	0.40
SURFACE							
Wetting tension (Min)		ASTM D-2578	Dyne / cm	44	44	44	44

The values given in this technical datasheet are typical performance data and are believed to be accurate. These are given in good faith but it is for the customer to satisfy of the suitability for its own particular purpose. JINDAL POLY FILMS LIMITED suggests the customer to confirm these values and product compatibility prior to their use and the company offers neither guarantee nor accepts any responsibility for the fitness of the product for any particular use.

JPFTM: JINDAL POLY FILMS TEST METHOD, MD: MACHINE DIRECTION, TD: TRANSVERSE DIRECTION

